

Gravitational Aharonov-Bohm effect in graphene

J. M. Fonseca, A. R. Pereira,* W. A. Moura-Melo, and D. H. T. Franco

Departamento de Física, Universidade Federal de Viçosa, Viçosa, 36570-000, Minas Gerais, Brazil

(Dated: April 20, 2008)

We study a kind of gravitational Aharonov-Bohm effect in a graphene sheet with a wedge removed and edges identified, i.e., a graphitic cone. The angular defect gives rise to a mismatch of the components of the graphene's relativistic charged quasiparticle wavefunctions (spinors) upon closed parallel transport around the (singular) cone tip. Such an effect should affect the basic electronic properties in “conical graphenes” as compared with their planar counterpart and it could be, in principle, detected experimentally. Measurements of the electronic transport in these graphitic materials and their relationships with the changes calculated in the quasiparticle wavefunctions could make available interesting probes to the Einstein theory of general relativity in two spatial dimensions. Therefore, we propose a way of verifying, in a microscopic scale, some predictions of a theory that is usually associated with incredible large objects such as planets, stars, black holes, galaxies and so on.

PACS numbers: 81.05.Uw, 73.63.Fg, 04.20.-q

The study of lower dimensional gravity is generally considered to be only an “academic” exercise, providing an useful arena for developing new ideas and insights, which are applicable to classical and even quantum theory of gravitation in $3 + 1$ dimensions [1]. In this letter we would like to suggest that the Einstein theory of gravitation in $2 + 1$ dimensions can be seen and even tested experimentally in possible realizable condensed matter materials, such as graphene. To understand our point of view, it would be instructive to review some properties of this material. As well known, graphene is a flat monolayer of carbon atoms tightly packed into a two-dimensional (2D) honeycomb lattice (see Fig. 1), or it can be viewed as an individual atomic plane pulled out of bulk graphite [2,3]. It is the first example of truly atomic 2D crystalline matter and is the basic building block for graphitic materials such as fullerenes (graphene balled into a sphere) or carbon nanotubes (graphene rolled-up in cylinders) [4,5,6]. From the point of view of its electronic properties, graphene is a zero-gap semiconductor, in which the low energy spectrum is formally described by the Dirac-like equation for a massless particle [3,7,8]

$$i\hbar\frac{\partial}{\partial t}|\Psi\rangle = v_F\vec{\sigma}\cdot\vec{p}|\Psi\rangle, \quad (1)$$

where v_F is the Fermi velocity, which plays the role of the speed of light ($v_F \approx c/300$), $\vec{\sigma} = (\sigma_x, \sigma_y)$ are the 2D Pauli matrices, $\vec{p} = -i\hbar\vec{\nabla}$ is the linear momentum operator and $|\Psi\rangle$ is a two-component spinor. Therefore, the quasiparticles (called massless Dirac fermions) can be seen as electrons that have lost their mass or as neutrinos that acquired the electron charge. In the honeycomb lattice of graphene, the two-component spinor $|\Psi\rangle$ is referred to as pseudospin since it is an index to indicate two interpenetrating triangular sublattices A e B , which is similar to spin index (up and down) in quantum electrodynamics (QED). It is common to regard the sublattice degree of freedom as a pseudospin, with the A sublattice




FIG. 1: (Color online) Graphene is a flat monolayer of carbon atoms having a honeycomb lattice, consisting of two interpenetrating triangular sublattices (green and red circles). Experimental techniques provide high-quality graphene crystallites up to $100\mu\text{m}$ in size, which is sufficient for most research purpose, including the one considered in this letter. The charge carries can travel thousands of interatomic distances without scattering.

being the “up” ($|+\rangle$) pseudospin state and B sublattice being the “down” ($|-\rangle$) pseudospin state, i.e.,

$$|+\rangle = \begin{pmatrix} 1 \\ 0 \end{pmatrix}; |-\rangle = \begin{pmatrix} 0 \\ 1 \end{pmatrix}. \quad (2)$$

Since $v_F \ll c$, it is a slow relativity system or a strong coupling version of QED since the graphene's dimensionless coupling constant ($e^2/\hbar v_F$) is on the order of unit, much larger than that of QED (the fine structure constant $e^2/\hbar c \approx 1/137$). All these properties make the graphene a very interesting system, which provides a way to probe QED phenomena by measuring its electronic properties. Several proposals for testing some predicted




FIG. 2: (Color online) Detaching a fraction of a graphene sheet to generate a deficit angle $2\pi\beta$.

but not yet observed phenomena in QED, including topics related to the Klein paradox [7,9], issues of vacuum polarization [10] and atomic collapse [11], etc, are under investigation in graphene. It becomes more exciting when one remembers that these probes are made in a low energy condensed matter system. All these potential connections between high energy and condensed matter physics inspire us to consider another question: could these strictly 2D materials actuate as a bridge between condensed matter physics and lower dimensional gravitation [more specifically, three-dimensional (2 + 1) gravitation]? It is not an empty problem because freely suspended graphene membrane is partially crumpled [12] and hence, it would be also interesting to study Dirac fermions in curved space. Here we will consider one of the simplest curved space, which is associated with the Schwarzschild solution in 2+1 dimensions: a space locally flat (with the Minkowski metric) but globally nontrivial (as described below). In this case, graphene would provide an appealing way to experimentally explore general relativity (GR) in two spatial dimensions.

To go further with our connection between graphene and gravitation we now summarize some aspects of general relativity in three space-time dimensions. It differs fundamentally from that of four dimensions. Indeed, it exhibits some unusual features, which can be deduced from the properties of the Einstein field equations and the Riemann curvature tensor $R^\mu_{\nu\epsilon\kappa}$ [1,13]. In regions which are free of matter (or wherever the momentum-energy tensor $T^{\mu\nu}$ vanishes), the space-time is locally flat when the cosmological constant is zero (the Einstein tensor $G^{\mu\nu}$ vanishes). However, this does not mean that a pointlike source has no gravitational effects: a light beam passing by a massive, pointlike source will be deflected [13,14,15,16] and parallel transport in a closed circuit around such a source will in general give nontrivial results [17]. Indeed, while the local curvature vanishes outside the sources, there are still nontrivial global effects. For instance, for the special case of a pointlike mass M sitting at rest in the origin, the line element is

given by

$$ds^2 = dt^2 - d\rho^2 - \rho^2 \alpha^2 d\theta^2, \quad (3)$$

with $0 \leq \theta < 2\pi$ and $\alpha = 1 - 4GM$ (G is the Newton's constant, which has dimensions of *length* rather than *length*² if one takes the natural units $\hbar = c = 1$). Note that although the situation looks trivial, the coordinate θ ranges from 0 to $2\pi\alpha$, indicating a deficit angle in space. Then, the space part of the metric is that of a plane with a wedge removed and edges identified; the unique 2D spatial geometry satisfying this description is the cone [13]. This is the point we would like to explore after the existence of 2D crystals whose excitations are massless Dirac fermions. Our proposal for association of graphene and gravitation is outlined in two parts: firstly, exploring the 2D character and flexibility of this material, the idea is to make a system in which one or more sectors are excised from a graphene (see Fig. 2) and the remainder is joined seamlessly (Fig. 3). In fact, the missed link of each carbon atom resting at the two edges of the remaining graphene sheet can be, in principle, covalently bounded. The nucleation and growth of curved carbon structures are still not well understood. It seems that the occurrence of pentagons, which yield 60° disclination defects in hexagonal graphitic network, is a key element in the puzzle. Particularly, considering the symmetry of a graphite sheet and the Euler's theorem, it can be shown that only five types of cones (incorporating one to five pentagons) can be made of a continuous sheet of graphite. Graphitic cones were already produced and all the types were synthesized [18,19]. For our purposes, it would be ideal that the incorporation of pentagons (if necessary) should be minimum (one to five pentagons may be tolerable) in the construction of a cone with a graphene sheet. Indeed, only a honeycomb lattice produces the peculiar energy-momentum relationship $E = v_F p$ and, therefore, pentagons may cause additional effects in the charge carriers beyond the one analyzed here. Secondly, with such a material one could study the properties of the massless Dirac fermions in a space which is locally described by the Minkowski metric but, however, possess nontrivial global effects that should affect the physical properties of these quasiparticles, bringing consequences to the electronic properties of the sample as whole. As a first discussion about this, we consider the changes that a closed-path parallel transport around the cone tip causes in the Dirac spinors $|\Psi\rangle$. Basically, it results in the Aharonov-Bohm effect but it does not occur in the presence of an electromagnetic field. Its origin is a defect in the material (the cone tip) which is very similar to the gravitational field generated by a static particle of mass M if the space were two-dimensional instead three-dimensional. Therefore, it will be called gravitational Aharonov-Bohm effect in graphene. Such phenomenon could also be used to probe GR in two spatial dimensions.

In the case of a conical graphene, it will be useful to substitute the gravitational term $4GM$ by the symbol β ,




FIG. 3: (Color online) If a wedge is removed from the graphene (see Fig. 2) and edges identified, a cone results. The motion of the charge carriers in an ideal conical graphene is equivalent to that of a massless Dirac particle in a gravitational field of a static particle of mass M in a 2+1 dimensional space-time.

which gives a deficit angle equal to $2\pi\beta$. It implies that the cone surface makes an angle $\delta = \arcsin(\beta)$ with its symmetry axis (the z -axis, which passes by the cone tip). The possible five graphitic cones mentioned earlier are then given by $2\delta = 19.2^\circ, 38.9^\circ, 60^\circ, 84.6^\circ, 112.9^\circ$. Our aim is, therefore, to see the influences that such a special graphene structure could induce on quasiparticle wavefunctions (spinors); surely, these influences may create new perspectives in the electronic transport properties, which are determined by the quasiparticles constrained to move in the conical surface. Hence, the first thing to do in this direction, is to examine the effects of closed-path parallel transport around the cone tip in the Dirac quasiparticle wavefunctions. It can be obtained by integrating the equations of parallel transport directly [17] or by using the path-ordered products of the relevant affine connection [20]. Thus, the two-component spinors representing the pseudospin in graphene is affected by parallel transport as follows

$$|\Psi(2\pi)\rangle = [\cos(\pi \sin \delta) - i\sigma_z \sin(\pi \sin \delta)]|\Psi(0)\rangle, \quad (4)$$

where σ_z is the Pauli matrix. Therefore, for a cone made with a single graphene sheet, the quasiparticle wavefunctions would experience an Aharonov-Bohm phase given by

$$|\Psi(2\pi)\rangle = \begin{pmatrix} \exp(-i\phi) & 0 \\ 0 & \exp(i\phi) \end{pmatrix} |\Psi(0)\rangle, \quad (5)$$

with $\phi = \pi \sin \delta$. Note that the spinors are very sensitive for detecting point defects in condensed matter (or equivalently, pointlike masses in gravitation). For instance, if $|\Psi(0)\rangle = p|+\rangle + q|-\rangle$ (p and q are constants), then, $|\Psi(2\pi)\rangle = p \exp(-i\phi)|+\rangle + q \exp(i\phi)|-\rangle$ and, therefore,

after the complete contour, the quasiparticles of A and B sublattices are mutually out of phase by $2\pi \sin \delta = 2\pi\beta$, which is exactly the deficit angle. Hence, the angular defect may give rise to a mismatch of the transport properties of electrons and holes in the A and B sublattices. Note that the phase difference in the spinor components has the required property of vanishing when the space becomes a plane, i.e., $\delta = 0$ ($\alpha = 1$). On the other hand, if $\delta \neq 0$, the electrons of one sublattice will be advanced in relation to the electrons of the other sublattice. This effect may manifest itself in fluctuations or concentration of charge carriers, which in turn alters several physical properties. For instance, in a planar graphene, it is known that the hopping of electrons between sublattices produces an effective magnetic field that is proportional, in magnitude and direction, to momentum measured from the Brillouin-zone corners. This effective field, which acts on the pseudospin, may suffer important changes in the conical graphene because a hopping of a quasiparticle, which was previously, say, in the A sublattice, will make it to become out of phase with all quasiparticles already occupying the B sublattice. Thus, if it is possible to measure the mismatch between the spinor components or its effects in the transport properties of the charge carriers, this system would provide an interesting place to probe some predictions of the Einstein theory of gravitation in two spatial dimensions.

In summary, we have considered the possibility of deforming a graphene sheet in a conical surface in order to check some predictions of general relativity in $2 + 1$ dimensions. Such a system makes possible the experimental study of relativistic massless quasiparticles with charge e on a two-dimensional surface of a cone, or equivalently, in the “gravitational field” (deficit angle) of a “pointlike particle” of mass M (cone tip). This surface is locally flat being described by the Minkowski metric, like the plane. There is no electromagnetic field (such as that of an infinitesimally thin solenoid [21]) and the “gravitational field” is concentrated inside the pointlike particle and vanishes identically outside of it. From a naive point of view it seems that in this configuration the charged quasiparticles could not be affected. Remarkably this is not the case: they respond to the “gravitational field” existing in a place to which they have no access. Therefore, it is similar to the usual Aharonov-Bohm effect in electromagnetism, but simulated as a gravitational field by a deficit angle incorporated in the material. It must have important influences on the electronic transport properties in “conical graphene” when electromagnetic fields are applied. In principle, the effect proposed here could be detected by interference experiments in structured materials and consequently these small systems could provide important probes for general relativity in dimensions smaller than four.

The authors thank CNPq, FAPEMIG and CAPES (Brazilian agencies) for financial support.

-
- * Electronic address: apereira@ufv.br
- ¹ J.D. Brown, *Lower Dimensional Gravity*, World Scientific, New Jersey (1988).
 - ² K.S. Novoselov, A.K. Geim, S.V. Morosov, D. Jiang, Y. Zhang, S.V. Dubonos, I.V. Grigorieva, and A.A. Firsov, *Science* **306**, 666 (2004).
 - ³ K.S. Novoselov, A.K. Geim, S.V. Morozov, D. Jiang, M.I. Katsnelson, I.V. Grigorieva, S.V. Dubonos, and A.A. Firsov, *Nature* **438**, 197 (2005).
 - ⁴ A.K. Geim and K.S. Novoselov, *Nature Mat.* **6**, 183 (2007).
 - ⁵ A. Catro-Neto, F. Guinea, and N.M. Peres, *Phys. World* **19**, 33 (2006).
 - ⁶ A.K. Geim and P. Kim, *Scient. Amer.* (April) 90 (2008).
 - ⁷ M.I. Katsnelson, K.S. Novoselov, and K. Geim, *Nature Phys.* **2**, 620 (2006).
 - ⁸ P.R. Wallace, *Phys. Rev.* **71**, 622 (1947).
 - ⁹ M.I. Katsnelson and K.S. Novoselov, *Sol. Stat. Comm.* **143**, 3 (2007).
 - ¹⁰ A. V. Shytov, M.I. Katsnelson, and L.S. Levitov, *Phys. Rev. Lett.* **99**, 236801 (2007).
 - ¹¹ A. V. Shytov, M.I. Katsnelson, and L.S. Levitov, *Phys. Rev. Lett.* **99**, 246802 (2007).
 - ¹² J. C. Meyer, A.K. Geim, M.I. Katsnelson, K.S. Novoselov, T.J. Booth, and S. Roth, *Nature* **446**, 60 (2007).
 - ¹³ , A. Staruszkiewicz, *Acta. Phys. Polon.* **24**, 734 (1963).
 - ¹⁴ S. Deser, R. Jackiw, and G. 't Hooft, *Ann. Phys. (N.Y.)* **152**, 220 (1984).
 - ¹⁵ S. Giddings, J. Abbott, and K. Kuchar, *Gen. Relativ. Gravit.* **16**, 751 (1984).
 - ¹⁶ A. Vilenkin, *Phys. Rev. D* **23**, 852 (1981).
 - ¹⁷ C.J.C. Burges, *Phys. Rev. D* **32**, 504 (1984).
 - ¹⁸ M. Ge, K. Sattler, *Chem. Phys. Lett.* **220**, 192 (1994).
 - ¹⁹ A. Krishnan, E. Dujardin, M.M.J. Treacy, J. Higdahl, S. Lynum, and T.W. Ebbesen, *Nature* **388**, 451 (1997).
 - ²⁰ V.B. Bezerra, *Phys. Rev. D* **35**, 2031 (1987).
 - ²¹ R. Jackiw, A.I. Milstein, S.-Y. Pi, and I.S. Terekhov, *cond-mat*, arXiv:0904.2046v1 (2009).